

Material Data

Specific Parameters of Standard Materials

				Ferroelectric soft PZT materials						Ferroelectric hard PZT materials				
			Unit	PIC151	PIC255/ PIC252	PIC155	PIC153	PIC152		PIC181	PIC184	PIC144	PIC241	PIC300
Physical and dielectric properties														
Density		ρ	g/cm ³	7.80	7.80	7.75	7.60	7.75		7.85	7.75	7.90	7.80	7.75
Curie temperature		T _C	°C	250	350	340	160	340		330	320	320	270	370
Coercive field strength (at 25 °C)		E _c	kV/mm	1.0	1.5	1.0	0.6	0.8						
Relative permittivity	in polarization direction	$\epsilon_{33}^T / \epsilon_0$		2500	1800	1750	4500	1350		1200	1200	1300	1750	1030
	⊥ to polarity	$\epsilon_{11}^T / \epsilon_0$		1980	1750	1850	3500	1100		1250	1250	1500	1500	960
Dielectric loss factor		tan δ	10 ⁻³	20	20	25	30	15		3	3	3	5	3
Electro-mechanical properties														
Coupling factor		k _p		0.62	0.62	0.62	0.62	0.48		0.56	0.55	0.60	0.55	0.47
		k _t		0.53	0.47	0.48	0.49	0.41		0.46	0.44	0.48	0.45	0.41
		k ₃₁		0.38	0.35	0.35	0.33	0.25		0.32	0.30	0.30	0.32	0.27
		k ₃₃		0.69	0.69	0.69	0.72	0.58		0.66	0.63	0.66	0.65	0.57
		k ₁₅		0.65	0.66	0.65	0.66	0.46		0.63	0.65	0.65	0.63	0.48
Piezoelectric charge coefficient		d ₃₁	10 ⁻¹² C/N	-210	-180	-165	-295	-90		-120	-99	-105	-140	-85
		d ₃₃	10 ⁻¹² C/N	500	400	360	600	240		265	220	225	300	190
		d ₁₅	10 ⁻¹² C/N	610	550	540	780	235		475	421	419	431	248
Piezoelectric voltage coefficient		g ₃₁	10 ⁻³ Vm/N	-10.1	-11.8	-12.8	-7.9	-8.7		-10.6	-10.7	-10.4	-9.2	-9.3
		g ₃₃	10 ⁻³ Vm/N	21.5	25.0	27.9	16.4	23.4		23.0	22.4	23.3	19.9	20.8
		g ₁₅	10 ⁻³ Vm/N	33.9	38.4	46.0	23.3	23.7		37.2	35.8	33.9	33.3	29.3
Acousto-mechanical properties														
Frequency coefficient (serial resonance fs)		N _p	Hz · m	1940	2000	1930	1940	2280		2270	2175	2170	2200	2400
		N _i	Hz · m	1500	1420	1500	1380	1570		1640	1590	1620	1590	1700
		N ₃	Hz · m	1360	1370	1340	1345	1530		1560	1560	1540	1550	1700
		N _t	Hz · m	1950	2000	1990	2020	2100		2110	2035	2035	2020	2100
		N _s	Hz · m	830	870	820	890	1130		1000	960	960	980	1050
Speed of sound		v ₁ ^E	m/s	3000	2840	3000	2760	3140		3280	3180	3240	3180	3400
		v ₃ ^D	m/s	3820	3690	3750	3650	3750		4060	3990	4090	3890	3990
		v ₅ ^D	m/s	2290	2340	2340	2260	2500		2400	2090	2450	2440	2330
		v _t ^D	m/s	3900	4000	3980	4040	4200		4220	4070	4070	4040	4200
Elastic compliance coefficient		S ₁₁ ^E	10 ⁻¹² m ² /N	16.4	16.0	16.1	17.2	13.1		11.8	12.2	12.4	12.6	11.2
		S ₃₃ ^E	10 ⁻¹² m ² /N	19.4	19.0	19.3	20.0	14.8		13.3	13.7	14.3	14.4	12.0
Elastic stiffness coefficient		C ₃₃ ^D	10 ¹⁰ N/m ²	15.7	15.4	15.8	15.5	16.6		17.0	15.8	16.6	15.5	16.3
Acoustic impedance (pressure wave in polarization direction)		Z ³³	MRayl (=10 ⁶ kg/m ² /s)	35.0	34.7	35.0	34.4	35.9		36.6	35.1	36.2	34.9	35.7
Mechanical quality factor		Q _m		100	80	80	50	100		2000	400	1000	500	1400
Temperature stability														
Temperature coefficient of ϵ_{33}^T (in the range of -20 to +125 °C)		TK ϵ_{33}	10 ⁻³ /K	4	3	4	15	2		3	4		3	2
Time stability (relative change of the parameters per decade of time in %)														
Relative permittivity		C _{ϵ}			-1.0	-3.0					-4.0			
Coupling factor		C _k	%		-1.0	-0.5					-2.0			

Modified materials on request.

1) Preliminary data, subject to change

Recommended operating temperature:
up to 50 % of Curie temperature

The following values are valid approximations for all PZT materials from PI Ceramic:

Specific heat capacity:
WK = approx. 350 J kg⁻¹ K⁻¹

Specific thermal conductivity:
WL = approx. 1.1 W m⁻¹ K⁻¹

Poisson's ratio (lateral contraction):
 σ = approx. 0.34

Coefficient of thermal expansion:
 α_3 = approx. -4 to -6 × 10⁻⁶ K⁻¹
(in the polarization direction, shorted)
 α_1 = approx. 4 bis 8 × 10⁻⁶ K⁻¹ (perpendicular to the polarization direction, shorted)

Static compressive strength:
>600 MPa

The data is determined using test pieces with the geometric dimensions laid down in EN 50324-2 standard and are typical values.

All data provided is determined 24 h to 48 h after the time of polarization at an ambient temperature of 23 ±2 °C.

A complete coefficient matrix of the individual materials is available on request. If you have any questions about the interpretation of the material characteristics, please contact PI Ceramic. Ceramic.

PI Ceramic GmbH
Lindenstraße
07589 Lederhose | Germany
Tel. +49 36604 882-0
Email info@piceramic.de
Web <http://www.piceramic.com>

Material Data

Parameters of Porous Materials

		Ferroelectric soft PZT materials			
			Unit	PIC255P63 ¹⁾	
Physical and dielectric properties					
Density		ρ	g/cm ³	6,3	
Curie temperature		T_C	°C	350	
Coercive field strength (at 25 °C)		E_c	kV/mm		
Relative permittivity	in polarization direction	$\epsilon^{T_{33}} / \epsilon_0$		970	
	⊥ to polarity	$\epsilon^{T_{11}} / \epsilon_0$			
Dielectric loss factor		$\tan \delta$	10 ⁻³	18	
Electro-mechanical properties					
Coupling factor		k_p		0.35	
		k_t		0.50	
		k_{31}			
		k_{33}			
		k_{15}			
Piezoelectric charge coefficient		d_{31}	10 ⁻¹² C/N		
		d_{33}	10 ⁻¹² C/N	316	
		d_{15}	10 ⁻¹² C/N		
Piezoelectric voltage coefficient		g_{31}	10 ⁻³ Vm/N		
		g_{33}	10 ⁻³ Vm/N	37	
		g_{15}	10 ⁻³ Vm/N		
Acousto-mechanical properties					
Frequency coefficient (serial resonance fs)		N_p	Hz · m	1790	
		N_1	Hz · m		
		N_3	Hz · m		
		N_t	Hz · m	1336	
		N_5	Hz · m		
Speed of sound		v_1^E	m/s		
		v_3^D	m/s		
		v_5^D	m/s		
		v_t^D	m/s	2670	
Elastic compliance coefficient		S_{11}^E	10 ⁻¹² m ² /N		
		S_{33}^E	10 ⁻¹² m ² /N		
Elastic stiffness coefficient		C_{33}^D	10 ¹⁰ N/m ²		
Acoustic impedance (pressure wave in polarization direction)		Z^{33}	MRayl (=10 ⁶ kg/m ² /s)	16.8	
Mechanical quality factor		Q_m		20	
Temperature stability					
Temperature coefficient of ϵT_{33} (in the range of -20 to +125 °C)		$TK \epsilon_{33}$	10 ⁻³ /K		
Time stability (relative change of the parameters per decade of time in %)					
Relative permittivity		C_ϵ			
Coupling factor		C_k	%		

Modified materials on request.

1) Porous ceramic, preliminary data, subject to change

Recommended operating temperature:
up to 50 % of Curie temperature

The following values are valid approximations for all PZT materials from PI Ceramic:

Specific heat capacity:
WK = approx. 350 J kg⁻¹ K⁻¹

Specific thermal conductivity:
WL = approx. 1.1 W m⁻¹ K⁻¹

Poisson's ratio (lateral contraction):
 σ = approx. 0.34

Coefficient of thermal expansion:
 α_3 = approx. -4 to -6 × 10⁻⁶ K⁻¹
(in the polarization direction, shorted)
 α_1 = approx. 4 bis 8 × 10⁻⁶ K⁻¹ (perpendicular to the polarization direction, shorted)

Static compressive strength:
>600 MPa

The data is determined using test pieces with the geometric dimensions laid down in EN 50324-2 standard and are typical values.

All data provided is determined 24 h to 48 h after the time of polarization at an ambient temperature of 23 ±2 °C.

A complete coefficient matrix of the individual materials is available on request. If you have any questions about the interpretation of the material characteristics, please contact PI Ceramic. Ceramic.

PI Ceramic GmbH
Lindenstraße
07589 Lederhose | Germany
Tel. +49 36604 882-0
Email info@piceramic.de
Web <http://www.piceramic.com>

Material Data

Parameters of Lead-Free Materials

		BNT materials				KNN materials	
		Unit	PIC700 ¹⁾	PIC701 ¹⁾		PIC753 ¹⁾	PIC758 ²⁾
Physical and dielectric properties							
Density		ρ	g/cm³	5.7	5.7	4.8	4.8
Curie temperature		T _c	°C	190 ³⁾	230 ³⁾	300	290
Coercive field strength		E _c	kV/mm	2.8	3.9	1.1	1.2
Relative permittivity	in polarization direction ⊥ to polarity	ε ^{T₃₃} / ε ₀		680	542	1341	850
		ε ^{T₁₁} / ε ₀		655	629	1222	950
Dielectric loss factor		tan δ	10 ⁻³	30	30	13	20
Electro-mechanical properties							
Coupling factor		k _p		0.14	0.13	0.53	0.43
		k _t		0.41	0.39	0.45	0.42
		k ₃₁		0.09	0.08	0.30	0.27
		k ₃₃		0.43	0.37	0.59	0.57
		k ₁₅		0.25	0.31	0.58	0.55
Piezoelectric charge coefficient		d ₃₁	10 ⁻¹² C/N	-20	-17	-118	-75
		d ₃₃	10 ⁻¹² C/N	100	71	241	170
		d ₁₅	10 ⁻¹² C/N	90	108	316	287
Piezoelectric voltage coefficient		g ₃₁	10 ⁻³ Vm/N	-3.3	-3.5	-9.9	-9.9
		g ₃₃	10 ⁻³ Vm/N	16.0	14.8	20.0	22.5
		g ₁₅	10 ⁻³ Vm/N	14.5	19.4	29.2	34.1
Akustomechanische Eigenschaften							
Frequency coefficient (serial resonance fs)		N _p	Hz · m	2984	3071	2869	
		N _i	Hz · m	2228	2302	2065	2296
		N _s	Hz · m	2420	2403	2445	2582
		N _t	Hz · m	2576	2503	2739	2803
		N _s	Hz · m	1516	1535	1555	1315
Elastic compliance coefficient		S ₁₁ ^E	10 ⁻¹² m²/N	8.8	8.2	12.2	9.8
		S ₃₃ ^E	10 ⁻¹² m²/N	9.1	7.5	13.6	11.6
Elastic stiffness coefficient		C ₃₃ ^D	10 ¹⁰ N/m²	15.1	13.5	17.2	17.8
Mechanical quality factor		Q _m		100	100	200	585
Temperature stability							
Temperature coefficient of ε _{T33} (in the range of -20 to +125 °C)		TK ε ₃₃	10 ⁻³ /K				
Time stability (relative change of the parameters per decade of time in %)							
Relative permittivity		C _ε					
Coupling factor		C _k	%				

Modified materials on request. The materials are not yet approved for production.

The reliability of lead-free materials must be re-evaluated in each application case. It may differ from the reliability of materials containing lead.

- 1) Preliminary data, subject to change
- 2) Material under development, no specifications
- 3) Depolarization temperature

The following values apply approximately for lead-free materials from PI Ceramic:

Specific heat capacity:
WK KNN = approx. 420 J kg⁻¹ K⁻¹
WK BNT = approx. 101 J kg⁻¹ K⁻¹

Specific thermal conductivity:
WL KNN = approx. 2.5 W m⁻¹ K⁻¹
WL BNT = approx. 1.4 W m⁻¹ K⁻¹

The data is determined using test pieces with the geometric dimensions laid down in EN 50324-2 standard and are typical values.

All data provided is determined 24 h to 48 h after the time of polarization at an ambient temperature of 23 ±2 °C.

A complete coefficient matrix of the individual materials is available on request. If you have any questions about the interpretation of the material characteristics, please contact PI Ceramic. Ceramic.

PI Ceramic GmbH
Lindenstraße
07589 Lederhose | Germany
Tel. +49 36604 882-0
Email info@piceramic.de
Web <http://www.piceramic.com>